

## Specification

Products Name		Yellow Stretch vinyl exam gloves powder-free				
Size	Weight (gm)	Length (mm) (min)	Palm Width (mm)	Thickness (mm)		
				Cuff	Palm	Finger-tip
S	4.8 $\pm$ 0.2	240 $\pm$ 5	85 $\pm$ 5	0.06 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
M	5.3 $\pm$ 0.2	240 $\pm$ 5	95 $\pm$ 5	0.06 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
L	5.8 $\pm$ 0.2	240 $\pm$ 5	105 $\pm$ 5	0.06 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
XL	6.3 $\pm$ 0.2	240 $\pm$ 5	115 $\pm$ 5	0.06 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
Tensile Strength			$\geq$ 16 MPA (Before aging), $\geq$ 16 (After aging)			
Elongation			$\geq$ 400%(Before aging), $\geq$ 400%(After Aging)			

Products Name		Yellow Stretch vinyl non-exam gloves powder-free				
Size	Weight (gm)	Length (mm) (min)	Palm Width (mm)	Thickness (mm)		
				Cuff	Palm	Finger-tip
S	4.5 $\pm$ 0.2	240 $\pm$ 5	85 $\pm$ 5	0.05 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
M	5.0 $\pm$ 0.2	240 $\pm$ 5	95 $\pm$ 5	0.05 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
L	5.5 $\pm$ 0.2	240 $\pm$ 5	105 $\pm$ 5	0.05 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
XL	6.0 $\pm$ 0.2	240 $\pm$ 5	115 $\pm$ 5	0.05 $\pm$ 0.02	0.08 $\pm$ 0.02	0.10 $\pm$ 0.02
Tensile Strength			$\geq$ 14 MPA (Before aging), $\geq$ 14 (After aging)			
Elongation			$\geq$ 380%(Before aging), $\geq$ 380%(After Aging)			